



Custom Color Premix Mortar Mixing Instructions:

Place material in a clean, suitable container (bucket, mixing box, wheelbarrow or power mixer).

For each 15 pounds of dry material use approximately 1 quart of water.

Add 3/4 of the mixing water and then blend in the dry ingredients.

Mix until all liquid is absorbed. This will be a very stiff mix and will allow the addition of more liquid to the mix without overwatering.

Add the balance of liquid required to achieve a smooth, lump-free and fully wetted mix. Do not overwater.

After initial mixing, allow the mix to rest and absorb all liquid for 2– 3 minutes.

Remix and apply.

1 quart = 32 oz.

Oz water / Lbs. of mortar mix

Size of Mortar bag (lbs.)	oz. water
1	2
5	11
10	21
20	43
15	32
30	64
40	85
80	171